

PRODUCT DATA SHEET

PRODUCT DESCRIPTION: Riley's 2-Component Polyamide Epoxy is intended for use on properly prepared surfaces for finishing or refinishing. Suitable applications include agricultural, construction, and industrial equipment, castings, metal fabrications, and tank exteriors.

ADVANTAGES:			CHARACTERISTICS:	APPLICATION:																		
WIDE BALANCE OF PERFORMANCE PROPERTIES: <ul style="list-style-type: none"> Excellent Adhesion Excellent Chemical Resistance Fast Recoat Time Good One Coat Protection Good Hardness And Film Toughness Excellent flow and leveling Good Humidity and Gasoline Resistant Excellent Salt Spray Performance Virtually any new or existing color standard can be matched Gloss can be matched to customer specifications Can be formulated for lower Hazardous Air Pollutants—HAP's 			GLOSS: Full Range VOLUME SOLIDS: 45-65% Varies by color VISCOSITY: 20-50 Seconds Zahn #3 SPREADING RATE: 600-900 SQ. FT./GAL. At 1 Mil, No Application Loss PACKAGE LIFE: 1 Years DRYING: Air Dry @ 77°F (25°C) 45% RH To Touch: 30 MINUTES To Handle: 60 MINUTES To Recoat: AFTER 60 MINUTES To Pack: 24 HOURS FORCE DRY: Up to 200°F for 30 minutes for most colors. RECOMMENDED FILM THICKNESS: WET: 4.0-8.0 MILS DRY: 2.0-4.0 MILS REDUCTION: Xylene, Toluene, D-100, D-150, N-Butyl-Acetate CLEAN UP: Toluene, Xylene or MEK. Warning. Residue from clean up is flammable.	APPLICATION PRECAUTIONS AND LIMITATIONS: Apply only when air, product or surface temperature is above 50°F (10°C) and when surface temperature is at least 5°F (3°C) above the dew point. Condensation will cause paint film failures. SURFACE PREPARATION: METAL: Apply to properly cleaned or treated metal surface. A solvent wipe to remove contaminates or sandblasting will work. Sand blasted metal may require more dry film thickness to fully cover blasted profile. Priming metal prior to topcoating is recommended for best overall properties. Preprimed surfaces may need to be lightly sanded and tacked off for best inner coat adhesion. Chemical treatment will improve the adhesion and performance properties of the paint. Treatment may consist of an iron phosphate chemical pretreatment. Riley manufactures several chemicals for surface preparation. ALUMINUM AND GALVANIZED IRON (UNTREATED): Prime with a vinyl wash primer then coat with an alkyd primer followed by a topcoat. WOOD (INTERIOR): No primer is required for properly prepared, previously painted surfaces. For new wood priming is recommended. Riley has specialty wood coating products that may work better. CONVENTIONAL SPRAY: Reduce to the desired viscosity using a solvent that has the appropriate reduction strength and dry time. Add with agitation. Spray at 40-60 psi atomizing pressure and 15-20 psi fluid pressure. Viscosity 25-55 seconds #2 EZ. AIRLESS SPRAY: Reduce to the desired viscosity using a solvent that has the appropriate reduction strength and dry time. Use .013"-0.019" tips and 12"-16" fan for best application. Viscosity 20-30 seconds #3 EZ. WARNING: Over spray residues will spontaneously combust. DIP: Not recommended.																		
			SOLVENT REDUCTION DATA: <table border="1"> <thead> <tr> <th>Solvent</th> <th>Comparative Spot Dry</th> <th>Reduction Strength</th> </tr> </thead> <tbody> <tr> <td>Toluene</td> <td>1 min. 5 sec.</td> <td>Strong</td> </tr> <tr> <td>Xylene</td> <td>2 min. 40 sec.</td> <td>Strong</td> </tr> <tr> <td>D-100</td> <td>6 min. 30 sec.</td> <td>Average</td> </tr> <tr> <td>D-150</td> <td>22 min.</td> <td>Average</td> </tr> <tr> <td>N-Butyl-Acetate</td> <td>2 min. 7 sec.</td> <td>Strong</td> </tr> <tr> <td>Methyl Ethyl Ketone</td> <td>35 sec.</td> <td>Strong. Used to enhance electrostatic wrap.</td> </tr> </tbody> </table>		Solvent	Comparative Spot Dry	Reduction Strength	Toluene	1 min. 5 sec.	Strong	Xylene	2 min. 40 sec.	Strong	D-100	6 min. 30 sec.	Average	D-150	22 min.	Average	N-Butyl-Acetate	2 min. 7 sec.	Strong
Solvent	Comparative Spot Dry	Reduction Strength																				
Toluene	1 min. 5 sec.	Strong																				
Xylene	2 min. 40 sec.	Strong																				
D-100	6 min. 30 sec.	Average																				
D-150	22 min.	Average																				
N-Butyl-Acetate	2 min. 7 sec.	Strong																				
Methyl Ethyl Ketone	35 sec.	Strong. Used to enhance electrostatic wrap.																				

KEEP OUT OF REACH OF CHILDREN

Consult MSDS for more information.

Revised 9-07-06

